



CBS

n-cyclohexyl -2- benzothiazole sulfenamide

CBS is a delayed action accelerator suitable for natural rubber and synthetic rubber; produces vulcanizates with high modulus and high tensile strength.

Specifications:

Appearance	Grey white to light yellow		
Form	Granular	Powder	Powder Oiled
*Initial Melt Point, °C.	97 min	97 min	97 min
*Final Melt Point, °C.	99 min	99 min	99 min
*Moisture, %	0.5 max	0.5 max	0.5 max
*Ash content, %	0.5 max	0.5 max	0.5 max
*Sieve residue (100 Mesh),%	NA	0.1 max	0.1 max
Sulfenamide, %	96 min	96 min	96 min
Total sulfur, %	23-24.7	23-24.7	23-24.7
*Content of oil, %	NA	NA	1-2
*Free amines (Cyclohexylamine), %	0.5 max	0.5 max	0.5 max
*Grain strength	2-4	NA	NA
Alcohol Insolubles, %	0.5 max	0.5 max	0.5 max
Specific Gravity, typical	1.29	1.29	1.29

* Actual data will be reported on Certificate of Analysis

03/2014

The information provided is without warranty regarding its accuracy or completeness. The information may not be valid under all conditions. The user has the final responsibility for determining the suitability of the product in a given application.