



CP-70

Chlorinated Paraffin Resin

Specifications:

Appearance	White to light yellow powder
*Chlorine content, %	70 ±1
*Softening point, °C	95 min
*Thermo stability C 175°C,% HCl	0.2 max
*Drying loss, %	1.0 max
*Sieve residue (20 mesh), %	0.02 max
*Acidity (mg KOH/g), typical	0.10
Specific Gravity, typical	1.60

***Actual Data will be reported on Certificate of Analysis**

03/2014

The information provided is without warranty regarding its accuracy or completeness. The information may not be valid under all conditions. The user has the final responsibility for determining the suitability of the product in a given application.