



CSM-40

Chlorosulfonated Polyethylene

Specifications:

Appearance	White Chips
*Chlorine content, %	33 - 37
*Sulfur content, %	0.8 - 1.2
*Mooney viscosity (ML1+ 4@ 100°C)	51 - 61

*Actual data will be reported on Certificate of Analysis

03/2014

The information provided is without warranty regarding its accuracy or completeness. The information may not be valid under all conditions. The user has the final responsibility for determining the suitability of the product in a given application.