



HRA 100

Aromatic C-9 hydrocarbon resin

HRA 100 is recommended for use in: coatings, paints, adhesives, rubber and inks. It is highly resistant to heat and ultraviolet.

Specifications:

Appearance	Yellow to amber granules
*Softening point, °C	100 - 120
*Color, Gardner	15 max
*Ash, %	0.1 max
*Bromine value (gBr/100g)	50 - 100
*Acidity, mg KOH/g	0.5 max
Specific Gravity	1.00 – 1.12

*Actual data will be reported on Certificate of Analysis.

09/2015

The information provided is without warranty regarding its accuracy or completeness. The information may not be valid under all conditions. The user has the final responsibility for determining the suitability of the product in a given application.