



## BDMC

### Bismuth Dimethyldithiocarbamate

BDMC is a secondary accelerator for rubber compounds. It will significantly increase the cure rate when used in conjunction with sulfur based cure systems utilizing thiazole or sulfenamide primary accelerators.

#### Specifications:

Appearance	Light yellow to golden powder
*Melting Point, °C	230 min
*Moisture, %	1.0 max
*Ash, %	40.0 – 45.0
*Residue on 100 mesh, %	0.50 max
*Bismuth content, %	33.0 – 38.0
Specific Gravity, typical	2.04

\* Actual data will be reported on Certificate of Analysis

03/2019

The information provided is without warranty regarding its accuracy or completeness. The information may not be valid under all conditions. The user has the final responsibility for determining the suitability of the product in a given application.