



DCP 40KE

40% dicumyl peroxide on kaolin clay agent for synthetic rubbers and plastics.

Specifications

Appearance	Light to off-white powder
*Activity, %	39 – 41
*Kaolin clay, %	59 – 61
*Active oxygen, %	2.32 min.
Specific gravity, typical	1.55

*Actual data will be reported on certificate of analysis

03/2014

The information provided is without warranty regarding its accuracy or completeness. The information may not be valid under all conditions. The user has the final responsibility for determining the suitability of the product in a given application.