



## DDCBP 50

Bis(2,4-dichlorobenzoyl) peroxide on oil

DDCBP 50 is an organic peroxide used for the low temperature (160 deg. F – 240 deg. F) crosslinking of silicone and fluorosilicone rubbers without external pressure.

### Specifications:

Appearance	White to off-white paste
*Peroxide content, %	49.0 – 51.0
*Active Oxygen Content, %	2.06 – 2.15
*pH	4 – 7
*Moisture, %	0.5 max.

\*Actual data will be reported on Certificate of Analysis

04/2017

The information provided is without warranty regarding its accuracy or completeness. The information may not be valid under all conditions. The user has the final responsibility for determining the suitability of the product in a given application.