



HRA 110

Aromatic C-9 hydrocarbon resin

HRA 110 is recommended for use in: EVA hot melt adhesives, solvent based adhesives, pressure sensitive adhesives and coatings. It is highly resistant to heat and ultraviolet, and is also water resistant. HRA-110 possesses a very low naphthalene content and is very light in color.

Specifications:

Appearance	Yellow to amber granules
*Softening point, °C	105 - 115
*Color, Gardner	6 max
*Ash, %	0.05 max
*Acidity, mg KOH/g	0.1 max
*Iodine value, gl/100 g	30 max
Specific Gravity	1.07 – 1.13

***Actual data will be reported on Certificate of Analysis.**

08/2017

The information provided is without warranty regarding its accuracy or completeness. The information may not be valid under all conditions. The user has the final responsibility for determining the suitability of the product in a given application.