



## TBPB

### Tert-butyl peroxybenzoate

TBPB is used for the curing of unsaturated polyester resins at elevated temperatures. It can also be used in combination with highly reactive peroxides as a kicker in formulations for pultrusion in the temperature range of 100 – 150 deg. C.

#### Specifications:

Appearance	Light yellow liquid
*Assay, %	98.0 minimum
*Active Oxygen Content, %	8.07 minimum
*Hydroperoxides as TBHP, %	0.1 maximum
*Inorganic + organic hydrolysable chloride, %	0.005 maximum

\*Actual data will be reported on Certificate of Analysis

01/2019

The information provided is without warranty regarding its accuracy or completeness. The information may not be valid under all conditions. The user has the final responsibility for determining the suitability of the product in a given application.