

## **VAL 40C**

VAL 40C is a dispersion of 40% Di-tert-butyl peroxide valerate on calcium carbonate. It is used as a crosslinking agent for synthetic rubbers, natural rubber and plastics. VAL 40C has high reactivity at lower processing and curing temperatures.

## **Specifications**

Appearance	White powder
*Activity, %	39 – 41
*Calcium carbonate content, %	59 - 61
*Active oxygen, %	4.15 – 4.36

\*Actual data will be reported on certificate of analysis

10/2018

The information provided is without warranty regarding its accuracy or completeness. The information may not be valid under all conditions. The user has the final responsibility for determining the suitability of the product in a given application.

PO Box 2628 • Stow, OH 44224 • 1-844-577-CHEM(2436) • 330-686-4450 • Fax: 330-686-5144 • rychemlic.com